



Loss factor measurements on plywood panels laminated with SWEDAC Damping layer DG-A 2

Spruce plywood	Volume weight ca 500 Kg/m ³				DG-A 2, 800 g/m ²		
Frequency	100	200	400	800	1200	1600	2000
6,5 + 6,5 mm	0,15	0,2	0,22	0,24	0,22	0,2	0,19
6,5 + 12 mm	0,13	0,2	0,22	0,22	0,24	0,26	0,17
6,5 + 15 mm	0,1	0,16	0,19	0,16	0,17	0,15	0,13
12 + 12 mm	0,15	0,25	0,29	0,24	0,23	0,24	0,2

