



Loss factor measurements on plywood panels laminated with SWEDAC Damping layer DG-A 2

Pine plywood

Volume weight ca 670 Kg/m³

DG-A 2, 900 g/m²

Frequency	100	200	400	800	1200	1600	2000
12 + 12 mm	0,15	0,23	0,27	0,29	0,27	0,24	0,22

